

TIGER SOMES IMPEX S.A.



Kotlas Pulp & Paper Mill

FULLY BLEACHED HARDWOOD KRAFT PULP

ECF

Typical Strength Properties

Beating rev.	Beating Degree SR (SR)	Tensile Index Nm/g (L)	Tear Index mN*m2/g (T)	Burst Index kPa*m2/g (B)
JOKRO	SR	Nm/g (L)	mN*m2/g (T)	kPa*m2/g (B)
0	15	15	2,5	0,2
2000	21	68	9,8	3,7
4000	29	77	9,7	4,4
6000	37	81	9,6	4,7
8000	44	83	9,5	4,9
10000	55	83	8,9	5,0

Physical Properties

Properties	Methods	Typical	Tolerance
Brightness	ISO 2470	89%	min. 88%
Dirt	ISO 5350-2	2,5 mm2/kg	max. 4 mm2/kg
Extractives	ISO 14453	0,25%	max. 0,4%
Ash	ISO 2144	0,25%	max. 0,4%

TIGER SOMES IMPEX S.A.

63 BISTRITEI STR. 405200 DEJ, CLUJ ROMANIA

TEL: +40 260 206 012 FAX: +40 264 223 239

www.tigersomes.ro

