

HARTIE SEMICHIMICA BELISCE

TECHNICAL SPECIFICATION

SC FLUTING

Basis weight ISO 536			CMT ISO 7263		SCT CD ISO 9895	
Typical value	Guaranteed value		Typical value	Guaranteed value	Typical value	Guaranteed value
	min. g/m ²	max. g/m ²				
g/m ²	min. g/m ²	max. g/m ²	N	min. N	kN/m	min. kN/m
112	109	115	220	215	2.3	2.0
120	116	124	260	240	2.4	2.2
127	123	131	270	255	2.5	2.3
140	136	144	300	280	2.7	2.5
150	145	155	330	300	3.0	2.6
175	170	180	360	330	3.3	2.8
200	194	206	380	350	3.5	2.9
Moisture (ISO 287): 8.0% +/- 1.5%						
Lab conditions: temperature: 23°C +/- 1°C; relative moisture: 50% +/- 2% (ISO 187)						