

TECHNICAL SPECIFICATION for KRAFTLINER PAPER ex MARIYSK mill

ISO 9001-2001

FACT VALUES

PROPERTY					
Substance, gr/m ²	110-120	118-132	132-148	141-159	163-187
Thickness, mm	0,16-0,21	0,18-0,24	0,21-0,27	0,23-0,29	0,27-0,33
Bursting Strength, KPa , not less	400	460	490	520	570
Cobb test; 60 sec., gr/m ² , not more	30	30	30	30	30
Breaking strength with ring crush in cross direction, N, not less		150		180	200
Moisture, %	6-9	6-9	6-9	6-9	6-9
Maximum trim, mm: PM.6 PM.7	4200 2750	4200 2750	4200 2750	4200 2750	4200 2750
Maximum External diameter, mm	1170	1170	1170	1170	1170